

**FINAL EXTENDED COMPOSITES DRILLED BY AVANTI
KITSAULT MINE (2009 DRILLING PROGRAM)**

Hole Number	From (m)	To (m)	Interval width (m)	Avg. Mo%	Avg. Ag (g/t)	Avg. W (ppm)	Avg. Pb (ppm)	Avg. Zn (ppm)	Avg. Bi	Avg. S%
K09-07-GT	4.57	87	82.43	0.194	3.91	72	176	606	90.7	1.61
	4.57	156	151.43	0.128	4.14	55	148	548	52.7	1.48
K09-12-GT	7.72	24	16.28	0.122	15.74	25	544	473	10.9	1.76
	7.72	186	178.28	0.064	7.77	19	325	535	10	1.65